## **Product Information**

## AVENO MBike 10W-30

0002-000708



## Description

AVENO MBike 10W-30 is a mineral oil-based engine oil with selected additives for demanding 4-stroke motorcycles. It is characterized by a very high oxidation stability, excellent lubricating film adhesion and reliability under any load and is specially designed fordesigned for wet and oil-lubricated clutches. AVENO MBike 10W-30 protects the engine from deposits and ensures a long service life.

## Instructions for use

AVENO MBike 10W-30 is suitable as motor oil for all air- and water-cooled 4-stroke motorcycles if a viscosity of 10W-30 is required. The operating instructions of the engine manufacturer must be observe

Quality classification					
Specification					
• API SN		• JASO MA2	• JASO MA2		
Properties					
Very good shear stability		<ul> <li>High safety reserves even under</li> </ul>	High safety reserves even under boundary lubrication conditions		
<ul> <li>Very good cold start properties</li> </ul>		<ul> <li>Optimum function of engine, c</li> </ul>	<ul> <li>Optimum function of engine, clutch and transmission</li> </ul>		
Prevention of premature wear		<ul> <li>Very good resistance to oxidati</li> </ul>	<ul> <li>Very good resistance to oxidation and high temperature engine deposits</li> </ul>		
<ul> <li>Tried and tested additives</li> </ul>					
Technical specifications					
Properties	Data	Unit	Testing under		
Kinematic Viscosity at 40°C	78.9	mm²/s	DIN 51659-2:2017-02		

Properties	Data	Unit	lesting under
Kinematic Viscosity at 40°C	78.9	mm²/s	DIN 51659-2:2017-02
Kinematic Viscosity at 100°C	12.1	mm²/s	DIN 51659-2:2017-02
Viscosity Index	148		DIN ISO 2909:2004-08
Appearance	BROWN		VISUELL
Density at 15°C	854	kg/m³	DIN EN ISO 12185:1997-11
Pour Point	-36	°C	ASTM D 7346:2015
Total Base Number (TBN)	7.9	mgKOH/g	ASTM D 2896:2021

Notice: To the best of our knowledge, all of the information provided was in accordance with the latest findings and developments of the Deutsche Ölwerke Lubmin GmbH. Our products are subject to continuous development. For this reason, our products, the manufacturing processes and all related information on this product page are subject to change at any time and without notice, unless customer-specific agreements exist. The data listed are based on standardized test procedures under appropriate laboratory conditions and are to be regarded as general, non-binding reference values.